



**FLOOR-TREK
INTERIOR/EXTERIOR ACRYLIC
URETHANE GLOSS 01263
LIGHT GREY FLOOR PAINT**

PRODUCT DATA

GENERIC TYPE: Acrylic Urethane Hybrid DTM

DESCRIPTION: A fast drying acrylic latex floor paint specifically formulated for use on interior and exterior surfaces. It has excellent adhesion, toughness and resistance to alkalinity, which makes this an ideal all purpose floor finish for a variety of substrates.

Features

- Waterbased
- Alkali Resistant
- Tough Flexible Film
- Fast Drying

RECOMMENDED USES: This product is ideal for indoor or outdoor application. It may be applied over new or old masonry surfaces such as patios, cellar floors, play rooms, porches, stairways, etc. This product may be used on wood floors with a suitable primer.

COMPATIBLE COATINGS: May be applied over properly prepared alkyd or acrylic finishes. See application instructions for substrate preparation.

NOT RECOMMENDED: Do not use on concrete driveways or garage floors where hot pick-up could occur.

Primers:

- McCormick 1st Step Interior/Exterior Acrylic Clear Brushing Lacquer Surface Conditioner 01242
- McCormick Underlok Interior/Exterior Acrylic Latex Multi-Purpose Primer 06452

PHYSICAL CHARACTERISTICS

- **Colors:** Light Grey
- **Vehicle Type:** Acrylic Urethane
- **VOC/VOS:** Less Than 150 Gms/L, 1.3 lbs/gal
- **Volume Solids (Avg.):** 35% ± 2%
- **Weight Solids (Avg.):** 47% ± 2%
- **Viscosity:** 95 KU
- **Suggested Film Thickness:**
 - Brush and Roll:** 4.5 mils wet, 1.5 mils dry
 - Spray:** 6 mils wet, 2.1 mils dry
- **Theoretical Coverage per Gallon:**
285 sq ft @ 2.0 mil DFT
- **Gloss Level:** 65-75% @ 60°
- **Sheen:** N/A
- **Drying Time @ 77°F & 50% R.H.:**
 - To Touch:** 30 minutes
 - Recoat:** 4 hours. Allow additional drying time during humid or cooler weather.
 - Foot Traffic:** 8 hours
 - Hard Dry:** 72 hours
 - Min. Surface/Air Temperature at Application:** 50°F
 - Max Surface/Air Temperature at Application:** 125°F
- **Flash Point:** 200°F
- **Heat Resistance:** 150°F Intermittent
- **Application:** Brush, Roller, or Spray
- **Thinning:**
 - Brush and Roller:** Not Recommended
 - Spray:** Up to One Pint of Water per Gallon
- **Clean Up:** Warm Water and Detergent
- **Packaging:** Gallon, Five Gallon
- **Weight per Gallon:** 10.7 – 10.9 lbs/gallon

APPLICATION INSTRUCTIONS

For the following surfaces, prime or finish with two coats of McCormick Floor-Trek Interior/Exterior Acrylic Urethane Gloss 01263 Light Grey Floor Paint.

SURFACE PREPARATION

All surfaces must be clean and free from dirt, dust, grease, oil, or peeling paint. A white powdery deposit (efflorescence) often found on masonry surfaces, should be completely removed with a stiff wire brush. All glossy surfaces should be lightly sanded and cleaned before painting.

Previously Painted Surfaces: Prime surface with McCormick 1st Step Acrylic Clear Brushing Lacquer Surface Conditioner 01242 and apply two finish coats of this product.

New or Unpainted Concrete Surfaces: All surfaces must be free of any laitance or efflorescence, clean, free of any adverse moisture conditions, have an appropriate surface profile, and be well cured before coating. Newly poured concrete must age at least 30 days before coating. Form release agents, sealers, curing compounds, and other foreign matter must be removed by mechanical scarification, or suitable chemical means to prepare surface before applying two full finish coats of this product.

Unpainted Wood: Prime with McCormick Underlok Interior Exterior Acrylic Latex Multi-Purpose Primer 06452 and apply two finish coats of this product.

APPLICATION

Mix the paint thoroughly. Apply by brush, roller, or spray. **Brush:** For best results, use a good quality nylon or polyester brush. **Roller:** Use a good quality 1/4" to 3/4" nap synthetic roller cover. Nap selection depends upon the substrate; the smoother the substrate, the shorter the nap. **Spray:** Thin with 1 pint of water per gallon when necessary. Do not apply if product, air and/or surface temperatures are below 50°F. Relative humidity should be below 90%. The use of additives to promote adhesion or ease of application is not recommended.

APPLICATION EQUIPMENT

- Apply by brush, roller, or spray.
- Manufacturers listed below are a guide. Others may be used. Changes in pressure and tip size may be required to achieve proper application.

Airless Spray

Pump: Titan / Graco

High pressure filter: 60 mesh

Fluid hose: 1/4" x 50'

Tips: 0.013" to 0.021"

Minimum pressure to avoid fingering is 2,000 psi

CAUTIONS --- Lead Hazard: WARNING!

If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to

www.epa.gov/lead.

CONTAINS CRYSTALLINE SILICA IN AN ENCAPSULATED STATE: If the dry paint film is sanded, the dust emitted can contain crystalline silica which has been shown to cause cancer under long-term exposure. **USE ONLY WITH ADEQUATE VENTILATION.** Wear appropriate respiratory protection when sanding or spraying this product. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, wear respiratory protection (NIOSH/MSHA TC23C or equivalent) or leave the area. Avoid contact with eyes and skin.

FIRST AID: If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

CONTAINER LABELING COMPLIES WITH APPLICABLE STATE RIGHT TO-KNOW ACTS. For additional safety and health information, please refer to the Material Safety Data Sheet (MSDS).

Rev Date 10/06

MANUFACTURED BY:

McCORMICK Paints

Commitment to Quality

2355 Lewis Avenue, Rockville, MD 20851

Technical Service 1-877-PAINT-55 — Ph: 301-770-3235 — Fax: 301-770-9814

www.mccormickpaints.com

PRODUCT DATA SHEET