



**McPOLYTHANE CLEAR  
POLYURETHANE GLOSS FINISH  
01198**

**PRODUCT DATA**

**GENERIC TYPE:** Polyurethane Alkyd

**DESCRIPTION:** McCormick McPolythane Clear Polyurethane Gloss Finish is an extremely durable, easy to apply polyurethane coating formulated with ultraviolet resistors that protects against harmful sun rays to maximize exterior and interior durability. It dries quickly to form a clear tough finish with excellent resistance to wear and staining from water, alcohol, food household chemicals, etc.

**Features:**

- Premium Quality
- Suitable for Wood Floors
- Resistant to Marring
- High Gloss Finish

**RECOMMENDED USES:** Highly recommended for application in hard use areas of hotels, hospitals, schools, homes, and factories. Suitable for wood floors, paneling, patio furniture, bar and table tops, cabinets, doors, etc.

**NOTE:** Satin and gloss McPolythane can be mixed together to change the sheen. Satisfactory results may not be obtained unless used as directed. McPolythane will give an amber tone to light colored stained or painted surfaces.

**COMPATIBLE COATINGS:** May be applied over properly prepared old finishes which have not been removed.

**NOT RECOMMENDED:** Do not use on house siding or other large exposed exterior surfaces. Do not use over shellac, lacquer, or sanding sealer that contains stearates or silicones.

**PHYSICAL CHARACTERISTICS**

**Colors:** Clear

**Vehicle Type:** Polyurethane Alkyd

**VOC/VOS:** Less than 450 g/L; 1.3 lb. /gal

**Volume Solids (Avg.):** 43.8% ± 2%

**Weight Solids (Avg.):** 50.3% ± 2%

**Viscosity:** 53-57 KU

**Suggested Film Thickness:**

**Brush and Roll:** 3.2 mils wet, 1.4 mils dry

**Spray:** 6 mils wet, 3 mils dry

**Theoretical Coverage per Gallon:**

500 sq ft @ 1.4 mils DFT

**Gloss Level:** 80 units @ 60°

**Sheen:** N/A

**Drying Time @77°F & 50% R.H.:**

**To Touch:** 4 hours

**Recoat:** 8 hours. Allow additional drying time during humid or cooler weather.

**Min. Surface/Air Temperature at Application:** 50°F

**Max. Surface/Air Temperature at Application:** 110°F

**Flash Point:** 150°F Intermittent

**Heat Resistance:** 250°F

**Application:** Brush, Roller or Spray

**Thinning:**

**Brush and Roller:** Not Recommended

**Spray:** Mineral Spirits up to One Pint per Gallon

**Clean Up:** Mineral Spirits

**Packaging:** Quart

**Weight per Gallon:** 7.2 - 7.5 lb. /gal

**This product is currently certified under MPI #56**

GREEN WISE®	LEED	SCAQMD	OTC
NO	NO	NO	YES

### APPLICATION INSTRUCTIONS

For the following surfaces, prime as indicated and finish with 3 coats of McCormick McPolythane Clear Polyurethane Gloss Finish 01198.

### SURFACE PREPARATION:

**Previously Stained or Polyurethaned Surfaces:** All surfaces must be internally dry, thoroughly clean, and free from dirt, grease, oil soap, wax and other surface contaminants that impair adhesion. Dull glossy surfaces by sanding. Clean sanded surfaces by wiping with clean rags wet with mineral spirits and allow to dry thoroughly. For best results apply 2 finish coats.

**New Wood:** Sand smooth and remove dust as for previously painted surfaces. Apply 3 finish coats.

**Stained Surfaces:** Make sure wood stain is completely dry before application. For best results apply 3 coats.

**APPLICATION:** Always stir well before use. Additives for ease of application or to promote adhesion are not recommended. Do not apply if material, substrate, or ambient temperature is below 50°F or above 110°F. Relative humidity should be below 90%. Apply by brush, roller, or spray. For best brush application results, use a quality synthetic filament brush. For roller application, use a ¼" nap cover. For spray application, thin with mineral spirits, up to one pint per gallon if necessary.

### APPLICATION EQUIPMENT:

- Apply by brush, roller, or spray.
- Manufacturers listed below are a guide. Others may be used. Changes in pressure and tip size may be required to achieve proper application.

#### **Airless Spray:**

Pump: Graco / Titan  
High Pressure Filter: 100 Mesh  
Fluid Hose: ¼" x 50'  
Tips: 0.013" - 0.015"  
Minimum pressure to avoid fingering: 2000 psi

### CAUTIONS --- Lead Hazard: WARNING!

If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**USE ONLY WITH ADEQUATE VENTILATION.** Wear appropriate respiratory protection when sanding or spraying this product. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, wear respiratory protection (NIOSH/MSHA TC23C or equivalent) or leave the area. Avoid contact with eyes and skin.

**First Aid:** If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

**CONTAINER LABELING COMPLIES WITH APPLICABLE STATE RIGHT-TO-KNOW ACTS.** For additional safety and health information, please refer to the Safety Data Sheet (SDS).