



INTERIOR LATEX FLAT 14 SERIES

PRODUCT DATA

GENERIC TYPE: Acrylic

DESCRIPTION: Match Point Interior Latex Flat is a professional quality flat coating formulated to provide a uniform smooth appearance and superior touch-up qualities.

Features:

- GREEN WISE® certified
- Very Low Spatter
- Quick Dry for Re-Coating
- Excellent Hiding
- Superior Touch-Up
- Low Odor, Low VOC

RECOMMENDED USES: Ideal for new construction, commercial building, renovation, and maintenance projects. For use on properly prepared interior drywall, cured plaster (30 days), and aged masonry surfaces (60 days).

COMPATIBLE COATINGS:

May be applied over properly prepared latex or alkyd/oil finishes. See application instructions for proper substrate primer.

Primers:

- McCormick 1st Step Interior Latex Enamel Undercoater and Primer Sealer 06441
- McCormick 1st Step Quick Drying Stain Sealer 01113
- McCormick 1st Step Interior Solvent Borne Acrylic Odorless Primer 06448 White
- McCormick Underlok Interior Exterior Acrylic Latex Multi-Purpose Primer 06452
- McCormick Acrylok Interior/Exterior 100% Acrylic Masonry Primer 06451.
- McCormick 1st Step Interior/Exterior White Metal Rust Inhibitive Primer 06453.

PHYSICAL CHARACTERISTICS

Colors: White, Standard Off Whites, and Pastels

Vehicle Type: Acrylic

VOC/VOS: Less than 50 g/L; 0.4 lb/gal

Volume Solids (Avg.): 32.5% ± 2%

Weight Solids (Avg.): 48.5% ± 2%

Viscosity: 90-95 KU

Suggested Film Thickness:

Brush and Roll: 4.0 mils wet, 1.0 mils dry

Spray: 6 mils wet, 2.1 mils dry

Theoretical Coverage per Gallon:

400 sq ft @ 1 mil DFT

Gloss Level: N/A

Sheen: 0.8 – 1.1 units @ 85°

Drying Time @ 77°F & 50% R.H.:

To Touch: 30 minutes

Recoat: 4 hours. Allow additional drying time during humid or cooler weather.

Min. Surface/Air Temperature at Application: 50°F

Max. Surface/Air Temperature at Application: 110°F

Flash Point: N/A

Heat Resistance: 150°F Intermittent

Application: Brush, Roller, or Spray

Thinning:

Brush and Roller: Not Recommended

Spray: Up to One Pint of Clean Water per Gallon

Clean Up: Warm Water and Detergent

Packaging: Gallon, Five Gallon

Weight Per Gallon: 11.4 - 11.6 lb/gal

NOT RECOMMENDED: Do not paint over wallcoverings. Vinyl wallcoverings can lose adhesion through age or from new or previous paint applications. Do not use as a trim paint, higher sheen finishes are recommended for these areas.



GREEN WISE®	LEED	SCAQMD	OTC
YES	YES	YES	YES

MATCH POINT INTERIOR LATEX FLAT 14 SERIES

APPLICATION INSTRUCTIONS

For the following surfaces, prime as indicated and finish with two (2) coats of Match Point Interior Latex Flat 14 Series.

SURFACE PREPARATION

Previously Painted Surfaces: All surfaces must be internally dry, thoroughly clean, and free from dirt, grease, kalsomine, wallpaper adhesive, loose and peeling paint, and other surface contaminants that might impair adhesion. Remove loose and peeling paint and sand edges smooth. Spackle nail holes and cracks. Sand and touch-up before finishing. Dull glossy areas by sanding. Prime with McCormick Unix Interior / Exterior Acrylic Latex Multi-Purpose Primer 06460. Any exposed substrates should be spot primed with appropriate McCormick primer as for unpainted surfaces listed below.

Unpainted Drywall: Spackle nail holes and cracks. Sand smooth and wipe clean. Self prime or prime with McCormick 1st Step Interior Latex Undercoater and Primer Sealer 06441.

Unpainted Plaster: Allow new plaster to age 30 days. Prime with McCormick Acrylok Interior/ Exterior 100% Acrylic Masonry Primer 06451.

Unpainted Masonry: Allow new masonry to age 60 days. **Brick and Smooth Concrete:** Prime with McCormick Acrylok Interior/Exterior 100% Acrylic Masonry Primer 06451. **Concrete Block:** Prime with McCormick Interior-Exterior Latex Block Filler 01015.

Unpainted Wood: Fill all nail holes and open joints with interior wood putty. Sand smooth and wipe clean. Prime with McCormick 1st Step Interior Latex Enamel Undercoater and Primer Sealer 06441.

Unpainted Galvanized Metal: Clean new galvanized surfaces by wiping surface with clean rags wet with mineral. Primed with McCormick Underlok Interior Exterior Acrylic Latex Multi-Purpose Primer 06452.

Unpainted Ferrous Metal: Prime with McCormick 1st Step Interior/Exterior White Metal Rust Inhibitive Alkyd Primer 06543.

APPLICATION

Always stir well before use. Additives for ease of application or to promote adhesion are not recommended. Do not apply if material, substrate, or ambient temperature is below 50°F or above 110°F. Relative humidity should be below 90%. Apply by brush, roller, or spray. For best brush application results, use a quality synthetic filament brush. For roller application, use a ½" to ¾" nap cover. For spray application, thin with clean water, up to one pint per gallon if necessary.

WASHING INSTRUCTIONS

Allow 30 days after application before washing. Remove common dirt stains by using a soft cloth or sponge, warm water and mild detergent. Do not apply too much hand pressure during washing; this will cause paint to burnish causing discoloration.

APPLICATION EQUIPMENT

- Apply by brush, roller, or spray.
- Manufacturers listed below are a guide. Others may be used. Changes in pressure and tip size may be required to achieve proper application.

Airless Spray:

Pump: Graco / Titan

High Pressure Filter: 60 Mesh

Fluid Hose: ¼" x 50'

Tips: 0.015" - 0.021"

Minimum pressure to avoid fingering: 2000 psi

CAUTIONS --- Lead Hazard: WARNING!

If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

USE ONLY WITH ADEQUATE VENTILATION. Wear appropriate respiratory protection when sanding or spraying this product. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, wear respiratory protection (NIOSH/MSHA TC23C or equivalent) or leave the area. Avoid contact with eyes and skin.

First Aid: If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, get medical attention immediately.

CONTAINER LABELING COMPLIES WITH APPLICABLE STATE RIGHT-TO-KNOW ACTS. For additional safety and health information, please refer to the Safety Data Sheet (SDS).

Rev 11/16

MANUFACTURED BY:

McCormick Paints
THE PAINT THE PROS USE

2355 Lewis Avenue, Rockville, MD 20851

Technical Service 1-877-PAINT-55 — Ph: 301-770-3235 — Fax: 301-770-9814

www.mccormickpaints.com

PRODUCT DATA SHEET